

More Products with More Performance™

# Torlon® 4203

polyamide-imide

Torlon 4203 is an unreinforced, lubricated, pigmented grade of polyamide-imide (PAI) resin for extrusion. It has the best impact resistance and greatest elongation of all the Torlon grades. Torlon PAI has the highest strength and stiffness of any thermoplastic up to 275°C (525°F). It has outstanding resistance to wear, creep, and chemicals.

Torlon 4203 offers outstanding electrical properties, which makes it ideal for high performance parts such as connectors,

switches and relays. In addition Torlon 4203 polyamide-imide can be used in applications such as thrust washers, spline liners, valve seats, bushings, bearings, wear rings, cams and other applications requiring strength at high temperature and resistance to wear.

- High Flow: Torlon 4203 EXT
- Higher Flow: Torlon 4203 HQ
- Highest Flow: Torlon 4203 HHQ

### General

Material Status	• Commercial: Active		
Availability	• Africa & Middle East • Asia Pacific	• Europe • North America	• South America
Features	• Ductile • Flame Retardant • Good Chemical Resistance	• Good Creep Resistance • Good Electrical Properties • Good Wear Resistance	• High Heat Resistance • High Temperature Strength • Ultra High Impact Resistance
RoHS Compliance	• RoHS Compliant		
Forms	• Pellets		
Processing Method	• Injection Molding	• Machining	• Profile Extrusion

### Physical

	Typical Value	Unit	Test Method
Specific Gravity	1.42	g/cm <sup>3</sup>	ASTM D792
Molding Shrinkage - Flow	0.60 to 0.85	%	ASTM D955
Water Absorption (24 hr)	0.33	%	ASTM D570

### Mechanical

	Typical Value	Unit	Test Method
Tensile Modulus			
--	4900	MPa	ASTM D1708
-- <sup>1</sup>	4480	MPa	ASTM D638
Tensile Strength <sup>1</sup>	152	MPa	ASTM D638
Tensile Stress	192	MPa	ASTM D1708
Tensile Elongation			
Break	15	%	ASTM D1708
Break <sup>1</sup>	7.6	%	ASTM D638
Flexural Modulus			ASTM D790
23°C	5030	MPa	
232°C	3590	MPa	
Flexural Strength			ASTM D790
23°C	241	MPa	
232°C	118	MPa	
Compressive Modulus	4000	MPa	ASTM D695
Compressive Strength	221	MPa	ASTM D695
Poisson's Ratio	0.45		ASTM E132

### Impact

	Typical Value	Unit	Test Method
Notched Izod Impact	140	J/m	ASTM D256
Unnotched Izod Impact	1100	J/m	ASTM D4812

Thermal	Typical Value	Unit	Test Method
Deflection Temperature Under Load 1.8 MPa, Unannealed	278	°C	ASTM D648
Thermal Conductivity	0.26	W/m/K	ASTM C177
Coefficient of Linear Thermal Expansion	0.000031	cm/cm/°C	ASTM D696
Electrical	Typical Value	Unit	Test Method
Surface Resistivity	5.0E+18	ohms	ASTM D257
Volume Resistivity	2.0E+17	ohm-cm	ASTM D257
Dielectric Strength	23	kV/mm	ASTM D149
Dielectric Constant			ASTM D150
60 Hz	4.20		
1 MHz	3.90		
Dissipation Factor			ASTM D150
60 Hz	0.026		
1 MHz	0.031		
Injection	Typical Value	Unit	
Drying Temperature	177	°C	
Drying Time	3.0	hr	
Suggested Max Moisture	0.050	%	
Rear Temperature	304	°C	
Nozzle Temperature	371	°C	
Mold Temperature	199 to 216	°C	
Back Pressure	6.89	MPa	
Screw Speed	50 to 100	rpm	
Screw L/D Ratio	18.0:1.0 to 24.0:1.0		

## Notes

Typical properties: these are not to be construed as specifications.

<sup>1</sup> Type I

**For assistance with an emergency involving products of Solvay Advanced Polymers, such as a spill, leak, fire, or explosion, call day or night:**

## **Emergency Health Information**

**USA** +1.800.621.4590

**International** +1.770.772.8577

## **Emergency Spill Information**

**USA** +1.800.424.9300 / +1.703.527.3887  
(CHEMTREC)

**Europe** +44 208.762.8322 (CARECHEM)

**China** +86.10.5100.3039

**All other Asian countries** +65.633.44.177

**For additional product information, technical assistance, and Material Safety Data Sheets (MSDS), call:**

**USA** + 1.800.621.4557/ +1.770.772.8760

**Europe** +49.211.5135.9000

**Japan** +81.3.5425.4300

**China & Southeast Asia** +86.21.5080.5080

To learn more about Solvay products and services, visit [www.SolvaySpecialtyPolymers.com](http://www.SolvaySpecialtyPolymers.com) or email us at:

Europe, Middle East and Africa : [SpecialtyPolymers.EMEA@solvay.com](mailto:SpecialtyPolymers.EMEA@solvay.com)

Americas : [SpecialtyPolymers.Americas@solvay.com](mailto:SpecialtyPolymers.Americas@solvay.com)

Asia and Australia : [SpecialtyPolymers.Asia@solvay.com](mailto:SpecialtyPolymers.Asia@solvay.com)

Solvay Specialty Polymers is comprised of the activities of the Solvay Advanced Polymers, Solvay Solexis and Solvay Padanoplast companies along with the Solvin PVDC products lines. To our actual knowledge, the information contained herein is accurate as of the date of this document. However the companies that comprise Solvay Specialty Polymers and none of their affiliates make any warranty, express or implied, or accepts any liability in connection with this information or its use. Only products designated as part of the Solviva® family of biomaterials may be considered as candidates for implantable medical devices; Solvay Specialty Polymers does not allow or support the use of any other products in any implant applications. This information is for use by technically skilled persons at their own discretion and risk and does not relate to the use of this product in combination with any other substance or any other process. This is not a license under any patent or other proprietary right. The user alone must finally determine suitability of any information or material for any contemplated use in compliance with applicable law, the manner of use and whether any patents are infringed. This information gives typical properties only and is not to be used for specification purposes. All companies comprising Solvay Specialty Polymers reserve the right to make additions, deletions or modifications to the information at any time without prior notification.

All trademarks and registered trademarks are property of the companies that comprise Solvay Specialty Polymers or their respective owners.

© 2011, Solvay Specialty Polymers. All rights reserved. R 3/25/2011

**Solvay**  
**Specialty Polymers**



a Passion for Progress®