

More Products with More Performance™

Torlon® 4203L

polyamide-imide

Torlon 4203L is an unreinforced, lubricated, pigmented grade of polyamide-imide (PAI) resin. It has the best impact resistance and greatest elongation of all the Torlon grades. Torlon PAI has the highest strength and stiffness of any thermoplastic up to 275°C (525°F). It has outstanding resistance to wear, creep, and chemicals.

Torlon 4203L resin offers outstanding electrical properties, which makes it ideal for high performance parts such as

connectors, switches and relays. In addition Torlon 4203L polyamide-imide can be used in applications such as thrust washers, spline liners, valve seats, bushings, bearings, wear rings, cams and other applications requiring strength at high temperature and resistance to wear.

- High Flow: Torlon 4203L-HF
- Low Flow: Torlon 4203L-LF

General

Material Status	• Commercial: Active		
Availability	• Africa & Middle East • Asia Pacific	• Europe • North America	• South America
Additive	• PTFE Lubricant		
Features	• Ductile • Fatigue Resistant • Flame Retardant • Good Chemical Resistance	• Good Creep Resistance • Good Electrical Properties • Good Wear Resistance • High Heat Resistance	• High Temperature Strength • Low Temperature Toughness • Ultra High Impact Resistance
Uses	• Aircraft Applications • Automotive Applications • Bushings • Connectors	• Electrical Parts • Electrical/Electronic Applications • Fasteners • Film	• Machine/Mechanical Parts • Oil/Gas Applications • Semiconductor Molding Compounds • Thrust Washer
RoHS Compliance	• RoHS Compliant		
Automotive Specifications	• ASTM D4000 PAI000 R03 A56316 GA140 Z1Z2Z3Z4Z5Z6, Dwg YC3P-7E195-AA • CHRYSLER MS-DB405 CPN3373 Color: Natural		
Forms	• Pellets		
Processing Method	• Injection Molding	• Machining	• Profile Extrusion

Physical

	Typical Value Unit	Test Method
Specific Gravity	1.42 g/cm ³	ASTM D792
Molding Shrinkage - Flow	0.60 to 0.85 %	ASTM D955
Water Absorption (24 hr)	0.33 %	ASTM D570

Mechanical

	Typical Value Unit	Test Method
Tensile Modulus		
--	4900 MPa	ASTM D1708
-- ¹	4480 MPa	ASTM D638
Tensile Strength ¹	152 MPa	ASTM D638
Tensile Stress	192 MPa	ASTM D1708

Mechanical	Typical Value	Unit	Test Method
Tensile Elongation			
Break	15	%	ASTM D1708
Break ¹	7.6	%	ASTM D638
Flexural Modulus			ASTM D790
23°C	5030	MPa	
232°C	3590	MPa	
Flexural Strength			ASTM D790
23°C	241	MPa	
232°C	118	MPa	
Compressive Modulus	4000	MPa	ASTM D695
Compressive Strength	221	MPa	ASTM D695
Poisson's Ratio	0.45		ASTM E132
Impact	Typical Value	Unit	Test Method
Notched Izod Impact	140	J/m	ASTM D256
Unnotched Izod Impact	1100	J/m	ASTM D4812
Thermal	Typical Value	Unit	Test Method
Deflection Temperature Under Load			ASTM D648
1.8 MPa, Unannealed	278	°C	
CLTE - Flow	0.000031	cm/cm/°C	ASTM E831
Thermal Conductivity	0.26	W/m/K	ASTM C177
Electrical	Typical Value	Unit	Test Method
Surface Resistivity	5.0E+18	ohms	ASTM D257
Volume Resistivity	2.0E+17	ohm·cm	ASTM D257
Dielectric Strength	23	kV/mm	ASTM D149
Dielectric Constant			ASTM D150
60 Hz	4.20		
1 MHz	3.90		
Dissipation Factor			ASTM D150
60 Hz	0.026		
1 MHz	0.031		
Injection	Typical Value	Unit	
Drying Temperature	177	°C	
Drying Time	3.0	hr	
Suggested Max Moisture	0.050	%	
Rear Temperature	304	°C	
Nozzle Temperature	371	°C	
Mold Temperature	199 to 216	°C	
Back Pressure	6.89	MPa	
Screw Speed	50 to 100	rpm	
Screw L/D Ratio	18.0:1.0 to 24.0:1.0		

Notes

Typical properties: these are not to be construed as specifications.

¹ Type I

For assistance with an emergency involving products of Solvay Advanced Polymers, such as a spill, leak, fire, or explosion, call day or night:

Emergency Health Information

USA +1.800.621.4590

International +1.770.772.8577

Emergency Spill Information

USA +1.800.424.9300 / +1.703.527.3887
(CHEMTREC)

Europe +44 208.762.8322 (CARECHEM)

China +86.10.5100.3039

All other Asian countries +65.633.44.177

For additional product information, technical assistance, and Material Safety Data Sheets (MSDS), call:

USA + 1.800.621.4557/ +1.770.772.8760

Europe +49.211.5135.9000

Japan +81.3.5425.4300

China & Southeast Asia +86.21.5080.5080

To learn more about Solvay products and services, visit www.SolvaySpecialtyPolymers.com or email us at:

Europe, Middle East and Africa : SpecialtyPolymers.EMEA@solvay.com

Americas : SpecialtyPolymers.Americas@solvay.com

Asia and Australia : SpecialtyPolymers.Asia@solvay.com

Solvay Specialty Polymers is comprised of the activities of the Solvay Advanced Polymers, Solvay Solexis and Solvay Padanaplast companies along with the Solvin PVDC products lines. To our actual knowledge, the information contained herein is accurate as of the date of this document. However the companies that comprise Solvay Specialty Polymers and none of their affiliates make any warranty, express or implied, or accepts any liability in connection with this information or its use. Only products designated as part of the Solviva® family of biomaterials may be considered as candidates for implantable medical devices; Solvay Specialty Polymers does not allow or support the use of any other products in any implant applications. This information is for use by technically skilled persons at their own discretion and risk and does not relate to the use of this product in combination with any other substance or any other process. This is not a license under any patent or other proprietary right. The user alone must finally determine suitability of any information or material for any contemplated use in compliance with applicable law, the manner of use and whether any patents are infringed. This information gives typical properties only and is not to be used for specification purposes. All companies comprising Solvay Specialty Polymers reserve the right to make additions, deletions or modifications to the information at any time without prior notification.

All trademarks and registered trademarks are property of the companies that comprise Solvay Specialty Polymers or their respective owners.

© 2011, Solvay Specialty Polymers. All rights reserved. R 3/25/2011

Solvay
Specialty Polymers



a Passion for Progress®