

Amodel® AE-8950

polyphthalamide

Amodel® AE-8950 is a 50% glass reinforced polyphthalamide (PPA) designed to work in the modern automotive electrical environment.

- Black: AE-8950 BK938

This grade features a high heat deflection temperature, high flexural modulus and high tensile strength, as well as excellent creep resistance and low moisture absorption.

General

Material Status	• Commercial: Active		
Availability	• Africa & Middle East • Asia Pacific	• Europe • Latin America	• North America
Filler / Reinforcement	• Glass Fiber, 50% Filler by Weight		
Features	• Glycol Resistant • Good Chemical Resistance • Good Creep Resistance • Good Dimensional Stability	• Good Stiffness • High Heat Resistance • High Stiffness • High Strength	• High Temperature Strength • Low Moisture Absorption • Non-Corrosive
Uses	• Automotive Electronics • Connectors	• Electrical Parts • Electrical/Electronic Applications	
RoHS Compliance	• Contact Manufacturer		
Appearance	• Black		
Forms	• Pellets		
Processing Method	• Injection Molding		

Physical	Typical Value	Unit	Test method
Density	1.68	g/cm ³	ISO 1183/A

Mechanical	Typical Value	Unit	Test method
Tensile Modulus (23°C)	19800	MPa	ISO 527-2
Tensile Stress (Break, 23°C)	280	MPa	ISO 527-2
Tensile Strain (Break, 23°C)	2.1	%	ISO 527-2
Flexural Modulus (23°C)	18500	MPa	ISO 178
Flexural Stress (23°C)	400	MPa	ISO 178
Flexural Strain	2.3	%	ISO 178

Impact	Typical Value	Unit	Test method
Charpy Notched Impact Strength (23°C)	12	kJ/m ²	ISO 179/1eA
Charpy Unnotched Impact Strength (23°C)	80	kJ/m ²	ISO 179/1eU
Notched Izod Impact Strength (23°C)	12	kJ/m ²	ISO 180/1A

Amodel® AE-8950

polyphthalamide

Thermal	Typical Value	Unit	Test method
Heat Deflection Temperature 1.8 MPa, Unannealed	300	°C	ISO 75-2/A
Glass Transition Temperature	135	°C	DSC
Melting Temperature	325	°C	ISO 11357-3

Flammability	Typical Value	Unit	Test method
Flame Rating ¹ (3.20 mm)	HB		UL 94

Injection	Typical Value	Unit
Drying Temperature	120	°C
Drying Time	4.0	hr
Suggested Max Moisture	0.030 to 0.060	%
Rear Temperature	316 to 330	°C
Middle Temperature	316 to 330	°C
Front Temperature	324 to 340	°C
Processing (Melt) Temp	330 to 350	°C
Mold Temperature	150 to 165	°C

Injection Notes

Injection Rate: 3-4 inch/second (7.5-10 cm/sec)

Holding Pressure: 50% of injection pressure

Storage:

- Amodel® compounds are shipped in moisture-resistant packages at moisture levels according to specifications. Sealed, undamaged bags should be preferably stored in a dry room at a maximum temperature of 50°C (122°F) and should be protected from possible damage. If only a portion of a package is used, the remaining material should be transferred into a sealable container. It is recommended that Amodel® resins be dried prior to molding following the recommendations found in this datasheet and/or in the Amodel® processing guide.

Notes

Typical properties: these are not to be construed as specifications.

¹ These flammability ratings are not intended to reflect hazards presented by these or any other materials under actual fire conditions.

www.solvay.com

SpecialtyPolymers.EMEA@solvay.com | Europe, Middle East and Africa

SpecialtyPolymers.Americas@solvay.com | Americas

SpecialtyPolymers.Asia@solvay.com | Asia and Australia

Safety Data Sheets (SDS) are available by emailing us or contacting your sales representative. Always consult the appropriate SDS before using any of our products.

Neither Solvay Specialty Polymers nor any of its affiliates makes any warranty, express or implied, including merchantability or fitness for use, or accepts any liability in connection with this product, related information or its use. Some applications of which Solvay's products may be proposed to be used are regulated or restricted by applicable laws and regulations or by national or international standards and in some cases by Solvay's recommendation, including applications of food/feed, water treatment, medical, pharmaceuticals, and personal care. Only products designated as part of the Solviva® family of biomaterials may be considered as candidates for use in implantable medical devices. The user alone must finally determine suitability of any information or products for any contemplated use in compliance with applicable law, the manner of use and whether any patents are infringed. The information and the products are for use by technically skilled persons at their own discretion and risk and does not relate to the use of this product in combination with any other substance or any other process. This is not a license under any patent or other proprietary right.

All trademarks and registered trademarks are property of the companies that comprise the Solvay Group or their respective owners.

© 2015 Solvay Specialty Polymers. All rights reserved.