



Torlon® 4645

polyamide-imide



Torlon 4645, an injection-moldable, wear-resistant grade of polyamide-imide (PAI), has been formulated to give outstanding wear resistance in lubricated wear applications.

Potential applications for Torlon 4645 polyamide-imide include thrust washers, seal rings, sliding vanes, bobbins, bushings, clutch rollers and pistons.

Torlon PAI has the highest strength and stiffness of any thermoplastic up to 275°C (525°F). It has outstanding resistance to wear, creep and chemicals.

General			
Material Status	• Commercial: Active		
Availability	• Africa & Middle East • Asia Pacific	• Europe • North America	• South America
Additive	• Carbon Fiber + PTFE Lubricant		
Features	• Flame Retardant • Good Chemical Resistance • Good Creep Resistance • Good Wear Resistance	• High Heat Resistance • High Stiffness • High Temperature Strength • Low Friction	• Self Lubricating • Semi Conductive
Uses	• Automotive Applications • Bearings	• Bobbins • Bushings	• Seals • Thrust Washer
RoHS Compliance	• Contact Manufacturer		
Forms	• Pellets		
Processing Method	• Injection Molding	• Machining	• Profile Extrusion

Physical	Typical Value	Unit	Test Method
Specific Gravity	1.57	g/cm ³	ASTM D792
Water Absorption (24 hr)	0.25	%	ASTM D570
Mechanical	Typical Value	Unit	Test Method
Tensile Modulus	18600	MPa	ASTM D638
Tensile Strength	114	MPa	ASTM D638
Tensile Elongation (Break)	0.80	%	ASTM D638
Flexural Modulus	12400	MPa	ASTM D790
Flexural Strength	154	MPa	ASTM D790
Compressive Strength	157	MPa	ASTM D695
Shear Strength			ASTM D732
23°C	85.5	MPa	
150°C	60.7	MPa	
Coefficient of Friction			ASTM D1894
-- 1	0.070		
-- 2	0.090		
Wear Factor			ASTM D3702
Lubricated: 0.375 m/s, 6.9 MPa (75 fpm, 1000 psi)	1.60	in ³ ·min ⁻¹ ·10 ⁻⁴ /ft·lb·hr	

Mechanical	Typical Value	Unit	Test Method
Lubricated: 4 m/s, 5.2 MPa (800 fpm, 750 psi)	0.300	in ³ ·min ⁻¹ - 10/ft·lb·hr	
Impact	Typical Value	Unit	Test Method
Notched Izod Impact	37	J/m	ASTM D256
Unnotched Izod Impact	110	J/m	ASTM D256
Thermal	Typical Value	Unit	Test Method
Deflection Temperature Under Load 1.8 MPa, Unannealed	281	°C	ASTM D648
Coefficient of Linear Thermal Expansion	0.000014	cm/cm/°C	ASTM D696
Injection	Typical Value	Unit	
Drying Temperature	177	°C	
Drying Time	3.0	hr	
Suggested Max Moisture	0.050	%	
Rear Temperature	304	°C	
Nozzle Temperature	371	°C	
Mold Temperature	199 to 216	°C	
Back Pressure	6.89	MPa	
Screw Speed	50 to 100	rpm	
Screw L/D Ratio	18.0:1.0 to 24.0:1.0		
Injection Notes			

Minimum drying times are: 3 hours at 350°F (177°C), 4 hours at 300°F (149°C), or 16 hours at 250°F (121°C).

Compression Ratio between 1:1 and 1.5:1

Begin hold pressure at a high setting 6,000-8,000 psi (41.37-55.16 MPa), for several seconds, then drop off to 3,000-5,000 psi (20.69-34.48 MPa), for the duration of the hold pressure sequence.

Molded parts must be post cured.

Notes

Typical properties: these are not to be construed as specifications.

¹ Lubricated: 4 m/s, 5.2 MPa (800 fpm, 750 psi)

² Lubricated: 0.25 m/s, 6.9 MPa (75 fpm, 1000 psi)