

G-11

Glass Epoxy

MIL-I-24768/3 / Type GEB



Physical Data

Specific Gravity	1.82
Tensile Strength	37,000 psi
Compressive Strength	63,000 psi
Flexural Strength	75,000 psi
Hardness - M Scale	112
Bond Strength	2,200 psi
Shear Strength	22,000 psi
Flammability Rating	94HB
Maximum Operating Temperature	356°F
Thermal Expansion Coefficient °C (x 10 ⁻⁵)	1.10
Water Absorption (24 Hours)	0.20
Izod Impact Strength (at 49°C -LW)	12.00

Product Info

G-11 is a halogen-free epoxy resin and woven fiberglass substrate laminate sheet. It qualifies for NEMA G11 and MIL-I-24768/3 requirements.

Available in rods, tubes, and sheets in various dimensions, lengths, diameters and thicknesses.


Capabilities

- High mechanical strength
- Electrical insulation
- Ease of fabrication

Electrical Data

Dissipation Factor - 106 cycles Condition A	0.020
Dielectric Constant - 106 cycles Condition A	5.00
Electric Strength V/MIL Condition A	900
Dielectric Breakdown - A	—
Permittivity - A	—

Contact Aztec Plastic Today!



**If you're looking for a high quality glass epoxy component,
let us be your complete solution.**

Call us today **312.733.0900** or visit **aztecplastic.com**